

# UV BASE 4602 LIGHT GREY 4250-678001

# AkzoNobel

<b>Type of Product</b> UV Curing Pigmented Primer	<b>Application Viscosity</b> Ready for use, delivery viscosity
<b>Area of Use</b> Furniture / Interior Joinery	<b>Applied Amount</b> Approx. 8-12 g/m <sup>2</sup> dry film
<b>Packaging</b> 4250-678001-206 - 20 L 4250-678001-816 - 1000 L	<b>Cleaning</b> 6500-008001 or 6800-001001 or 6800-005001
<b>UV Curing Products</b> When using UV-Curing products on absorbing substrates like MDF or porous woods, unreacted material can be retained in the substrate. If the product is used on these substrates, attention should be given to the choice of sealer. Consult our Technical Staff for recommendations relating to your specific line conditions. UV lacquers react when exposed to ultra-violet radiation, including sunlight.	<b>Empty Packaging</b> Disposal according to local regulations.
<b>Binder</b> Acrylate	<b>UV Curing</b> Cures by UV radiation only. Can be gelled with Ga or LED lamp. The curing depends on various conditions, i.e. applied amount, UV intensity, line speed, temperature, etc.
<b>Solid Contents</b> Approx. 100 % by weight	<b>Additional Drying Information</b> Please contact our Technical Staff for specific data concerning curing conditions on your line.
<b>Delivery Viscosity</b> 500-900 mPas CAP2000 #3/400 @ 35 °C	<b>Color</b> IKEA LIGHT GREY
<b>Density</b> 1,70 +/- 0,05 kg/l	<b>HSE Information</b> Use safety gloves and safety eyewear/face shield during the work. See Safety Data Sheet for further information.
<b>Shelf Life</b> 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.	
<b>Storage Conditions</b> Between 15 and 25 °C under clean and dry conditions. Keep from freezing. Protect from direct sunlight.	
<b>Methods</b> Smooth roller coater	
<b>Application Conditions</b> Between 30 - 45 °C for substrate, air and material at approx. 55 % R.H.	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-10-29 / 8

EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

# AkzoNobel