

**TECHNOLOGY**

PU Acrylic

**PRODUCT TYPE**

Topcoat

**PRODUCT DESCRIPTION**

A lightfast solventborne 2k topcoat with good mechanical and chemical resistance. This product is suitable for bleached wood.

- good mechanical and chemical resistance
- suitable for bleached wood
- open and closed pores
- lightfast
- high solid content

**COLOUR**

Clear

**GLOSS LEVEL (APPROX. GU @ 60°)**

05 / 10 / 15 / 30 / 60 / 90

**SYSTEM RECOMMENDATIONS**

1st layer (recommended options)

- Quantum S130
- Quantum T234
- Quantum T260

2nd layer

- Quantum T234

**PACK SIZES**Q-T234-1 - 5 L  
Q-T234-2 - 20 L**SHELF LIFE**

24 months

**STORAGE CONDITIONS**

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

**SOLID CONTENT**

29% -34% depending on gloss level

**DENSITY (SPECIFIC WEIGHT)**

0,97 +/- 1%

**DELIVER VISCOSITY**

35 sec DIN 4 mm. +/- 5

**PREPARATION OF SUBSTRATES**

Raw wooden surfaces. Graduated sanding of wood. Carefully remove the sanding dust. Coarse-pore wood must be brushed out	P120, P150, P180
Stained wooden surfaces	Sand prior to staining
Open-pore coatings	Sealing with Quantum S130
Closed-pore coatings	Close the pores by repeated application of Quantum sealer, e.g., Quantum IS160
Exotic wood / woods rich in extractives Wood or MDF in wet rooms	Priming with Quantum IS160 in a ratio of 5:1
Pigmented topcoats made with Quantum Color	Topcoat must be applied without intermediate sanding after 3 hours up to a maximum of 8 hours

**APPLICATION TEMPERATURE**

Between 20-25 °C for substrate, air and material at approx. 55 % R.H.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-07-15 / 40

# QUANTUM T234

**sikkens**

WOOD COATINGS

INTERIOR

## HARDENER

Hardener	Ratio (by weight)
HPU6301	10%




## THINNING

TPU9302-M / TPU9303-S

## APPLICATION METHOD

Spray application airmix/airless, spray application high/low pressure, curtain coater


## APPLICATION

			
Spray pressure (bar)	1.5 - 2.0	110 - 130	
Nozzle size (mm)	1.6 - 2.0	10 - 20	
Thinner to be added (%)	20 - 30	10 - 20	0 - 10
Processing viscosity DIN 4mm (sec.)	15 - 17	18 - 20	6 - 10
Layer Thickness (g/m <sup>2</sup> )	100 - 140	100 - 140	100 - 140

## DRYING TIME @ 20°C

Dust dry	At least 15 minutes
Touch dry	At least 45 minutes
Sandable	At least 1 hour
Ready for transport	At least 12 hours

## TEST STANDARDS

	DIN 68861/1C Chemical exposure of furniture surfaces
---	--

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-07-15 / 40