

## TÉCNOLOGIA

PU Acrílico

## TIPO DE PRODUCTO

Acabado

## DESCRIPCIÓN DEL PRODUCTO

Capa de acabado 2K base disolvente, de secado muy rápido con pigmento resistente a la luz que proporciona un aspecto natural en la aplicación. Modificado con cera para lograr un efecto sedoso al tacto.

- buena capacidad de relleno
- apariencia natural
- secado muy rápido
- no amarillea
- resistente a la luz en todas las condiciones
- modificado con cera para lograr un efecto sedoso al tacto



## COLOR

Transparente

## NIVEL DE BRILLO (APROX. GU @ 60°)

05 / 20 / 35

20 L

## VIDA ÚTIL

24 meses

## CONDICIONES DE ALMACENAJE

Mantener las latas bien cerradas, en un lugar bien ventilado, con temperatura controlada entre 10 y 30°C

## CONTENIDO SOLIDO

30%

## DENSIDAD (PESO ESPECÍFICO)

0,95±1% Kg/l

## VISSCOSIDAD DE ENTREGA

70±10% Din Copa 4

## PREPARACIÓN DEL SUBSTRATO



Superficies de madera en bruto. Lijado graduado de madera. Retire con cuidado el polvo de lijado. La madera de poro grueso debe cepillarse

P120,  
P150,  
P180

## TEMPERATURA DE APLICACIÓN

Entre 20-25 °C para sustrato, aire y material a aprox. 55 % H.R.

## ENDURECEDOR (EN PESO)

HPU6301	10%	hasta 8h
---------	-----	----------

## DILUIR

TPU9302-M / TPU9303-S

## MÉTODO DE APLICACIÓN

Aplicación por pulverización airmix/airless, aplicación por pulverización de alta/baja presión

## APLICACIÓN

Presión de pulverización (bar)	1.5 - 2.0
Tamaño de boquilla (mm)	1.6 - 2.0
Diluyente a añadir (%)	20 - 30
Viscosidad de aplicación DIN 4 mm (seg.)	15 - 17
Grosor de la Capa (g/m²)	100 - 140

## TIEMPO DE SECADO @ 20°C




Seco al polvo	Al menos 10 minutos
Seco al tacto	Al menos 25 minutos

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-25 / 5

## ESTÁNDARES DE PRUEBA

	DIN 68861/1B Exposición química de muebles superficies
	EN 71-3 Migración de metales pesados solubles / DIN 53160 Parte 1 y 2 Resistencia a la saliva y sudor
	Materiales y objetos en contacto con alimentos / plásticos según UNI EN 1186-5: 2003

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-25 / 5