

# POLYDUR COLOR P320

**sikkens**

WOOD COATINGS

INTERIOR

## TÉCNOLOGIA

Póliester

## TIPO DE PRODUCTO

Primer

## DESCRIPCIÓN DEL PRODUCTO

Imprimación blanca de poliéster 3K de secado rápido y base disolvente con gran poder cubriente. Adecuado para usar con acabados de PU de alto brillo que se utilizan a menudo en muebles de interior y de cocina en general.

- alta capacidad de relleno
- sin contracción (ideal como capa base para alto brillo)
- poros cerrados
- amarillamiento moderado



## COLOR

Blanco

20 KG

## VIDA ÚTIL

6 meses

## CONDICIONES DE ALMACENAJE

Mantener las latas bien cerradas, en un lugar bien ventilado, con temperatura controlada entre 10 y 30°C

## CONTENIDO SOLIDO

84.9% ± 1%

## DENSIDAD (PESO ESPECÍFICO)

Aprox. 1,45 ± 1% g/l at 20°C

## VISSCOSIDAD DE ENTREGA

55 ± 5 DIN 6 mm

## PREPARACIÓN DEL SUBSTRATO

	Superficies de madera en bruto.	P120, P150, P180
	Maderas exóticas / maderas ricas en extractivos Madera o MDF en cuartos húmedos	Sellar con QIS160 o SIS130 antes.

## ENDURECEDOR (EN PESO)

AUP6571	2%	hasta 30 minutos al agregar 20% de TPU9500-F	Acelerante
HUP6500	2%		Catalizador

## DILUIR

TUP9500-F

## MÉTODO DE APLICACIÓN

Aplicación a pistola

## APLICACIÓN

Presión de pulverización (bar)	1.5 - 3.0
Tamaño de boquilla (mm)	2.5-3.0
Diluyente a añadir (%)	15-25
Viscosidad de aplicación DIN 4 mm (seg.)	18-20 DIN 4 mm
Grosor de la Capa (g/m²)	250-350

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1

# POLYDUR COLOR P320

**sikkens**

WOOD COATINGS

INTERIOR

## TIEMPO DE SECADO @ 20°C

Seco al polvo	Al menos 50 minutos
Seco al tacto	Al menos 2 horas
Lijable	Al menos 14 horas
Tiempo de evaporación después de la aplicación	20 minutos

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1