

GLASS ADHESION PROMOTER AGENT

sikkens

WOOD COATINGS

INTERIOR

TÉCNOLOGIA

Base Solvente y Base Agua

TIPO DE PRODUCTO

Aditivo

INSTRUCCIONES GENERALES

La cantidad a añadir es del 2%. El producto debe removerse bien. El recubrimiento de los vidrios pretratados debe llevarse a cabo rápidamente, a más tardar dentro de las 6 horas. Para lograr una adhesión óptima al vidrio, la limpieza a fondo del sustrato de vidrio a recubrir es un requisito básico

DESCRIPCIÓN DEL PRODUCTO

Aditivo para la adhesión al cristal. Aplicable a algunas pinturas base disolvente y base agua en combinación con reductor de tensión de superficie.



0.5 L

VIDA ÚTIL

12 meses en el envase original sin abrir

CONDICIONES DE ALMACENAJE

Mantener las latas bien cerradas, en un lugar bien ventilado, con temperatura controlada entre 10 y 30°C

CONTENIDO SOLIDO

98% ± 1%

DENSIDAD (PESO ESPECÍFICO)

0,98 +/- 1%

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1