

**DURACIDCOLOR DC-T430-30-B01
(TRÄFF 30 B01)
2150-761301**

AkzoNobel

Type of Product 2-pack Acid Curing Pigmented Top Coat	Shelf Life 24 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.																				
Area of Use Furniture / Interior Joinery	Storage Conditions Between 15 and 25 °C under clean and dry conditions.																				
Additional Information The product is thixotropic with good sag resistance, which also makes it suitable for application on edges and profiles.	Methods Spraying																				
Packaging 2150-761301-050 - 5 l 2150-761301-120 - 10.8 l 2150-761301-700 - 200 l 2150-761301-800 - 1000 l	Mixing Ratio Coating : Hardener 10 : 1 (by volume)																				
Suitable Primer US Grund, Proff / Träff Primer	Application Viscosity Conventional spraying: 20-30 sec DIN cup 4 @ 23 °C																				
Notes DURACIDCOLOR-T430 is adjusted to Wood Coatings Color System. The product contains ≤ 1% aromatic solvents.	Applied Amount Approx. 110 g/m ² wet film																				
Binder Alkyd / Amino resins	Potlife Approx. 24 Hours @ 20 °C																				
Solid Contents Approx. 73 % by weight	Cleaning Cleaning thinner or 6500-008001																				
Delivery Viscosity Thixotropic	Empty Packaging Disposal according to local regulations.																				
Density Approx. 1,27 kg/l	Thermal Drying <table border="1"> <thead> <tr> <th>Temperature (°C)</th> <th>20</th> <th>40</th> <th>60</th> <th>80</th> </tr> </thead> <tbody> <tr> <td>Time to (min)</td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Sandable</td> <td>240</td> <td>120</td> <td>60</td> <td>20</td> </tr> <tr> <td>Stackable.</td> <td>1200</td> <td>240</td> <td>60</td> <td>20</td> </tr> </tbody> </table>	Temperature (°C)	20	40	60	80	Time to (min)					Sandable	240	120	60	20	Stackable.	1200	240	60	20
Temperature (°C)	20	40	60	80																	
Time to (min)																					
Sandable	240	120	60	20																	
Stackable.	1200	240	60	20																	
Hardener 7200-003001	Additional Drying Information The drying depends on various conditions, i.e. application method, applied amount, time, etc. Please contact our Technical Staff for specific data concerning curing conditions on your line.																				
Thinner 6500-004001																					

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-03-15 / 4

DURACIDCOLOR DC-T430-30-B01 (TRÄFF 30 B01)

Gloss

Approx. 30 GU @ 60°. The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.

Color

Base 01 White

HSE Information

See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-03-15 / 4

EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood