

Quantum Q-T260-15



Product description

Description	Two-pack, solvent-thinnable, non yellowing, acrylic-based clear PU topcoat.
-------------	---

Range of application

Description	Almost all wooden furniture in the interior. Open- or closed-pore coatings. Usable as final coat on pigmented topcoats with QuantumColor QC-T. Usable as self seal lacquer.
-------------	---

Product data

Product code	Q-T260-15
Packaging size	5l 20 l
Viscosity at delivery DIN 4 mm (sec.)	25 ± 2
Shelf life - Original container unopened	at least 2 years

Gloss levels

Product number	Gloss level	DIN 67530 Angle of 60°
Q-T260-15	semi matt	15 ± 2

Preparation of substrates

	Raw wooden surfaces. Graduated sanding of wood. Carefully remove the sanding dust. Coarse-pore wood must be brushed out.	P120, P150, P180
	Stained wooden surfaces	Sand prior to staining
	Closed-pore coating	Close the pores by repeated application of Quantum sealer, e.g., Q-IS160 or Q-S170
	Exotic wood / woods rich in extractives Wood or MDF in wet rooms	Priming with Quantum QT-IS160 in a ratio of 5:1.
	Pigmented topcoats made with QuantumColor QC-T	Topcoat must be applied without intermediate sanding after 3 hours up to a maximum of 8 hours

Processing

	Stir thoroughly!
	Mix and apply the product as described under "Hardener Thinner Additives".

Hardener - Thinner - Additives

	Hardening	10% of HPU 6300
	Dilution	TPU 9300-F fast drying TPU 9301-S slow drying
	Pot life 20°C, 65% rel. humidity	

Application







Spray pressure (bar)	1.5 - 2.0	110-130
Nozzle size (mm)	1.6-2.0	0.23-0.28
Thinner to be added (%)	10-20	
Processing viscosity DIN 4mm (sec.)	18-20	25
Coverage per application (g/m²)	90-120	120
Coverage (m²/l)	6-10	7

Drying time @ 20°C

Dust dry	at least 15 minutes
Touch dry	at least 45 minutes
Sandable	at least 1 hour
Ready for transport	at least 12 hours

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2022-07-12 / 10

Quantum

Test standards	
	DIN 68861/1B Chemical exposure of furniture surfaces
	EN 71-3 Migration of soluble heavy metals
	General appraisal certificate with regard to low flammability according to DIN 4102/B1 on hardly inflammable B1-tested wooden particle boards, even veneered.
	Hardly inflammable according to the Marine Equipment Directive MED 2014/90/EC.
	Requirement for furniture surfaces in regards to their resistance to temperature changes
	Tox Control - The label for low-emission furniture coatings

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2022-07-12 / 10

EMEA HQ
Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Germany ● www.akzonobel.com/wood

AN_204450_060919