

TECHNOLOGIA

Poliester

RODZAJ PRODUKTU

Podkład

OPIS PRODUKTU

Szybkoschnący rozcieńczalnikowy trzyskładnikowy biały podkład poliestrowy z dobrą siłą krycia. Odpowiedni do użycia z wysokopołyskowymi lakierami nawierzchniowymi PU, często używany na meblach wewnętrznych i kuchennych.

- dobra siła krycia
- bez skurczu (idealny podkład pod wysoki połysk)
- zamknięte pory
- umiarkowane żółknięcie

**KOLOR**

Biały

20 KG

OKRES PRZECHOWYWANIA

6 miesięcy

WARUNKI PRZECHOWYWANIA

Trzymać puszki szczelnie zamknięte, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

84.9% ± 1%

GĘSTOŚĆ (CIĘŻAR WŁĄŚCIWY)

Ok. 1,45 ± 1% kg/l przy 20°C

LEPKOŚĆ HANDLOWA

55 ± 5 DIN 6 mm

PRZYGOTOWANIE SUBSTRATÓW

	Powierzchnie z surowego drewna.	P120, P150, P180
	Drewno egzotyczne / drewno bogate w ekstrakty. Drewno lub MDF w wilgotnych pomieszczeniach	Zaizolować najpierw przy użyciu QIS160 lub SIS130.

UTWARDZACZ (WAGOWO)

AUP6572	2%	do 30 minut przy dodatku 20% TPU9500-F	Akcelerator
HUP6501	2%		Katalizator

ROZCIEŃCZANIE

TUP9500-F

METODA APLIKACJI

Aplikacja natryskiem

APLIKACJA

Ciśnienie natrysku (bar)	1.5 - 3.0
Rozmiar dyszy (mm)	2.5-3.0
Dodatek rozcieńczalnika (%)	15-25
Lepkość robocza DIN 4 (s)	18-20 DIN 4mm
Grubość warstwy (g/m²)	250-350

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1

POLYDUR COLOR P320

sikkens
WOOD COATINGS
INTERIOR

CZAS SCHNIĘCIA @ 20°C

Pyłosuchy	Przynajmniej 50 minut
Suchy w dotyku	Przynajmniej 2 godziny
Szlifowalny	Przynajmniej 14 godzin
Czas flash off po nałożeniu	20 minut

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1