

## TECHNOLOGIA

PU Akrylowy

## RODZAJ PRODUKTU

Lakier nawierzchniowy

## OPIS PRODUKTU

Bardzo szybko schnący rozcieńczalnikowy dwuskładnikowy lakier nawierzchniowy z światłotrwałymi pigmentami nadający naturalny wygląd. Modyfikowany woskiem dla jedwabistego efektu haptycznego.

- dobre wypełnianie
- naturalny wygląd
- bardzo szybko schnący
- nieżółknący
- światłotrwały w każdych warunkach
- modyfikowany woskiem dla jedwabistego efektu haptycznego



## KOLOR

Bezbarwny

## POZIOM POŁYSKU (OK.GU @ 60°)

05 / 20 / 35

20 L

## OKRES PRZECHOWYWANIA

24 miesiące

## WARUNKI PRZECHOWYWANIA

Trzymać puszkę szczelnie zamkniętą, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

## ZAWARTOŚĆ CIAŁ STAŁYCH

30%

## GĘSTOŚĆ (CIĘŻAR WŁAŚCIWY)

0,95±1% Kg/l

## LEPKOŚĆ HANDLOWA

70 ± 10% DIN Cup 4

## PRZYGOTOWANIE SUBSTRATÓW



Powierzchnie z surowego drewna. Stopniowane szlifowanie drewna. Dokładnie usunąć pył po szlifowaniu. Drewno otwartoporowe należy wyszczotkować.

P120,  
P150,  
P180

## TEMPERATURA APLIKACJI

Pomiędzy 20-25 °C dla substratu, powietrza i materiału przy ok. 55% W.W.

## UTWARDZACZ (WAGOWO)

HPU6301	10%	Do 8 godzin
---------	-----	-------------

## ROZCIEŃCZANIE

TPU9302-M / TPU9303-S

## METODA APLIKACJI

Aplikacja natryskiem airmix/airless, aplikacja natryskiem wysoko/niskociśnieniowym

## APLIKACJA

Ciśnienie natrysku (bar)	1.5 - 2.0
Rozmiar dyszy (mm)	1.6 - 2.0
Dodatek rozcieńczalnika (%)	20 - 30
Lepkość robocza DIN 4 (s)	15 - 17
Grubość warstwy (g/m²)	100 - 140

## CZAS SCHNIĘCIA @ 20°C




Pyłosuchy	Przynajmniej 10 minut
Suchy w dotyku	Przynajmniej 25 minut

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-25 / 5

#### NORMY TESTOWE

	DIN 68861/1B Narażenie chemiczne powierzchni meblowych
	EN 71-3 Migracja rozpuszczalnych metali ciężkich / DIN 53160 Część 1 i 2 Odporność na ślinę i pot
	Materiały i artykuły w kontakcie z żywnością / plastiki na podstawie UNI EN 1186-5: 2003

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-25 / 5