

# AQUA POSITIVE STAIN

**sikkens**

WOOD COATINGS

INTERIOR

## TECHNOLOGY

Waterborne

## PRODUCT TYPE

Stain

## PRODUCT DESCRIPTION

Waterborne pigment reactive stain giving an positive effect on softwood and warm old effect on oak.

- Lightfast dyes and pigments
- Mix with TI colorants to produce a wide range of colours
- Overcoat with Solventborne/Waterborne clear coat



## COLOUR

Clear

## PACK SIZES

1 L  
5 L

## SHELF LIFE

12 months

## STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

## SOLID CONTENT

10.1% ± 1%

## DENSITY (SPECIFIC WEIGHT)

1,03 +/- 1%

## DELIVER VISCOSITY

12 ± 2 Viscosity at delivery DIN 4 mm (sec.)

## PREPARATION OF SUBSTRATES

	Graduated sanding of wood Carefully remove the sanding dust. Coarse-pore wood must be brushed out.	P120, P150, P180
	Optionally wet with water. Sand or smoothen after drying overnight.	

## APPLICATION METHOD

Spray application and brush

## APPLICATION

Spray pressure (bar)	1.0-1.5
Nozzle size (mm)	0.8-1.3

## DRYING TIME @ 20°C

Overcoatable	At least 12 hours
--------------	-------------------

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 9