

SOLIDO IS150

sikkens
WOOD COATINGS
INTERIOR

TECHNOLOGY

PU Alkyd


PRODUCT TYPE

Sealer

PRODUCT DESCRIPTION

Solventborne 2K insulating sealer for use on exotic, tanning-rich wood to prevent bleeding of tanning on the surface.

- to avoid discolouration of stains due to the oxidation caused by Polydur sealers



COLOUR

Clear

PACK SIZES

5050-006001-050 - 5 L
5050-006001-200 - 20 L

SHELF LIFE

18 months

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

11.3% ± 1%

DENSITY (SPECIFIC WEIGHT)

0,91 +/- 1%

DELIVER VISCOSITY

45 ± 5 sec DIN cup 2 mm

PREPARATION OF SUBSTRATES



Raw wooden surfaces.

P120, P150, P180

HARDENER

Hardener	Ratio (by weight)
HPU6218	100%

THINNING

TPU9302-M

APPLICATION METHOD

Spray application

APPLICATION

	
Spray pressure (bar)	1.5 - 2.0
Nozzle size (mm)	1.6 - 2.0
Processing viscosity DIN 4mm (sec.)	8-10
Layer Thickness (g/m²)	100 - 120

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-02-26 / 15