

# DURACID T260

**sikkens**

WOOD COATINGS

INTERIOR

## TECHNOLOGY

Acid Curing

## PRODUCT TYPE

Topcoat

## PRODUCT DESCRIPTION

Quick drying 2K solventborne topcoat with a formaldehyde-free formula.

- quick drying
- aromatic &lt; 1%
- formaldehyde-free
- moderate yellowing



## COLOUR

Clear

## PACK SIZES

DT260 - 20 L

## SHELF LIFE

24 months in original, unopened package

## STORAGE CONDITIONS

Between 15 and 25°C under clean and dry conditions.

## SOLID CONTENT

Gloss 10: Approx. 44 % by weight  
Gloss 30: Approx. 33 % by weight

## DENSITY (SPECIFIC WEIGHT)

Gloss 10: Approx. 1,00 kg/l  
Gloss 30: Approx. 0,96 kg/l

## DELIVER VISCOSITY

Gloss 10: Approx. 80-100 sec DIN Cup 4 @ 23 °C.  
Gloss 30: Approx. 55 sec DIN Cup 4 @ 23 °C.

## APPLICATION TEMPERATURE

Between 20-25 °C for substrate, air and material at approx. 55 % R.H.

## HARDENER

Hardener

HAC6404 10:0,5 by volume

## THINNING

TAC9400-M; TAC9402-S

## APPLICATION METHOD

Spray application airmix/airless, spray application high/low pressure, curtain coater

## APPLICATION

			
Processing viscosity DIN 4mm (sec.)	15-40 sec DIN cup 4 @ 20 °C	15-40 sec DIN cup 4 @ 20 °C	15-40 sec DIN cup 4 @ 20 °C
Layer Thickness (g/m²)	Max. 2 x 110 g/m² wet film	Max. 2 x 110 g/m² wet film	Max. 2 x 110 g/m² wet film

## DRYING TIME @ 20°C

Sandable	At least 1 hour
Stackable	At least 3 hours

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-06-28 / 14