

## Aqualit A-IS180



Product data	
Packaging size	5l
Viscosity at delivery DIN 4 mm (sec.)	40 ± 2
Shelf life – Original container unopened	at least 1 year
VOC Directive EC limit value for this product (cat. A/e): 130 g/l (2010)	This product contains max. 74 g/l VOC.

Preparation of substrates		
	Raw wooden surfaces. Exotic wood / woods rich in extractives Wood or MDF in wet rooms	P120, P150, P180
	Stained wooden surfaces	Sand prior to staining

Processing	
	Stir thoroughly!
	Mix and apply the product as described under "Hardener Thinner Additives".

Hardener - Thinner - Additives		
	Hardening	20% of HWA 6000
	Dilution	TWA 9000-F or tap water
	Pot life 20°C, 65% rel. humidity	up to 4 hours

Application		
Spray pressure (bar)	1.5 - 2.0	60-90
Nozzle size (mm)	1.8-2.0	0.25-0.33
Thinner to be added (%)	20	10-20
Processing viscosity DIN 4mm (sec.)	40	40-50
Coverage per application (g/m²)	100-140	100-140
Coverage (m²/l)	5 - 7	5 - 7

Drying time @ 20°C	
Dust dry	at least 30 minutes
Touch dry	at least 1 hour
Sandable	at least 4 hours

Special notes	
The product is frost-sensitive. Do not store and transport under 5° C	
Do not use any rusting tools.	
Always keep the containers closed in order to protect the contents against drying-out.	
CO2 is released during the reaction of the two components. For that reason, the hardened product must not be poured into a closed container.	
PU hardeners are affected by moisture. Always store the hardener in tightly closed original batches.	
When using PU hardeners, always follow the safety instructions on the label.	
PU hardeners can be stored in the closed original container at a cool and dry place for a maximum of one year.	
By diluting the product with TWA 9000-F, drying is accelerated and the flow and wetting properties of the lacquer are improved.	
After sanding, greasy wood rich in ingredients, such as teak, should first be washed-out with the thinner TPU9300-F by means of a lint-free cloth in the direction of the wood grain.	

Test standards	
	Requirements to the surfaces of kitchen furniture according to DIN68930 regarding the resistance under changing climatic conditions

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2020-07-13 / 73