

## Quantum

(ICLA 217.30.00)

### Q-T236



#### Product description

Description	One-component, solventborne, lightfast clear topcoat on acrylate basis. The product produces a deep matt natural wood surface without grain emphasis. The timber is protected but still looks untreated.
-------------	--

#### Range of application

Description	Many wooden furniture indoors without major chemical and mechanical stress. For open-pore coatings only. Usable as self seal lacquer. Not suitable as top coat on pigmented lacquers.
-------------	---

#### Product data

Product code	Q-T236
Packaging size	5l 20 l
Viscosity at delivery DIN 4 mm (sec.)	35 ± 5
Solid content in % base material	6 ± 1
Specific weight in kg/l at 20°C	approx. 0.88
Shelf life - Original container unopened	at least 2 years

#### Gloss levels

Product number	Gloss level	DIN 67530 Angle of 60°
Q-T236	dead matt	0-2

#### Preparation of substrates

	Raw wooden surfaces. Graduated sanding of wood. Carefully remove the sanding dust. Coarse-pore wood must be brushed out.	P120, P150, P180
--	--	------------------------

#### Processing

	Stir thoroughly!
	Mix and apply the product as described under "Hardener Thinner Additives".

#### Hardener - Thinner - Additives

	Dilution	TPU 9303-S (910.73) slow drying - 0-50%
--	----------	---

#### Application

Spray pressure (bar)	1.5 - 2.0	110-130
Nozzle size (mm)	1.6-2.0	0.23-0.28
Processing viscosity DIN 4mm (sec.)	16-20	16-20
Coverage per application (g/m²)	100-120	100-120
Coverage (m²/l)	8-10	8-10

#### Drying time @ 20°C

Dust dry	at least 20 minutes
Touch dry	at least 40 minutes
Sandable	at least 1 hour
Ready for transport	at least 12 hours

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-01-16 / 18